

P.T. INDO LYSAGHT



ISO 9001:2008 - ISO 14001:2004 CERTIFIED COMPANY
BY SAI GLOBAL
QEC. No: 21628 – CEM. No: 20428



Head Office : Komplek Puri Mutiara
Blok A No.23-25
Jl. Griya Utama, Sunter Agung
Jakarta Utara 14350 – Indonesia
Telephone : (021) 65311333 (Hunting)
Facsimile : (021) 65313666

Chemical Formula Zn
Appearance Grey Powder

Analytical Value

Total Zinc Zn
Metallic Zinc Zn
Pb
Cd
Fe

Zinc Dust F-500		Zinc Dust F-1000		Zinc Dust F-2000		Zinc Dust F-3000	
Typical	Specification	Typical	Specification	Typical	Specification	Typical	Specification
99.3%	99.0%	99.0%	99.0%	99.2%	99.0%	99.1%	99.0%
96.5%	96.0%	96.0%	95.5%	96.0%	95.5%	95.5%	95.0%
0.05%	0.15%	0.02%	0.15%	0.02%	0.15%	0.02%	0.15%
0.01%	0.05%	0.01%	0.05%	0.01%	0.05%	0.01%	0.05%
0.002%	0.005%	0.002%	0.005%	0.002%	0.005%	0.002%	0.005%

Average Particle Size

7.5 ± 0.5 micron	4.9 ± 0.5 micron	4.3 ± 0.5 micron	3.7 ± 0.5 micron
------------------	------------------	------------------	------------------

Style of Packing

Can/Pail/Drum 50 kg. 500 kg
Bulk bag 400 / 500 kg
Pre-pack / Other packing on request.

Physical properties

Molecular weight 65.37
Melting point 419 C
Boiling point 907 C
Specific gravity 7.1
Bulk density 2.3 g/cc

Application Zinc Rich Paint /Zinc primers

Storage Storage in warehouse, avoid contact with flame
and water. Keep below 40 degree C
Stored in dry and air tight containers or bags.

Marketing Office : KYOKUTO METAL SINGAPORE Pte Ltd
9A, JURONG PIER ROAD SINGAPORE 619162 TEL : 65-62682055 FAX : 65-62680360

Factory : Jl. Kapten Tole Iskandar Km. 2 Sukmajaya (Depok) Cimanggis – Bogor
Telephone : 77828971, 77828974, 77828968, - Fax. : 77829011